

OMKYD F – 322 (ADS PAINT)**PRODUCT DESCRIPTION**

OMKYD F - 322 is single pack air drying cum Stoving Synthetic Enamel used as final coat. The product is recommended as top coat after applying suitable primer where mild chemical resistance is required. This product is suitable for Indoor application and it has limitation in outdoor application. Recommended as top coat for OEM industries where mild chemical or corrosion is required. This is a low cost product.

SALIENT FEATURES

- Single Pack Air Drying
- Economical
- Easy to Apply
- Can be top coated with alkyd based top coats

TECHNICAL

| | |
|-----------------------|---|
| TYPE | Single Pack Synthetic type |
| COMPOSITION | Synthetic Alkyd type |
| APPLICATION | Brush / Roller / Airless spray |
| VOLUME SOLIDS | 30 ± 3% |
| RECOMMENDED DFT | 20 to 25 microns per coat |
| THEORETICAL COVERAGE | 12 to 15 sq. met per coat per lit |
| DRYING TIME | Touch Dry ..2Hours, Dry to handle5 to 8 Hours, Hard Dry....Overnight |
| OVER COATING INTERVAL | Minimum overnight, Maximum 4 Days |
| FLASH POINT | Above 22 C |
| SHADES | All IS & RAL Shades also variety of shades as per requirement |
| PACKING | 20 Lits, 4 Lits |
| THINNER/CLEANER | OMKAR G P THINNER |
| FINISH | GLOSSY / SEMI GLOSSY / MATT FINISH |
| STORAGE LIFE | 12 months stored in cool, dry condition away from Flame and Sun in original sealed container as supplied. |

SURFACE PREPARATION

This is a top coat which is applied over Primer or intermediate coats. The surface of the substrate should be free from oil, moisture and dust. Aged coating should be roughened by emery paper grade 220. For better bonding, all surface should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504. For more details contact our representative. It is advisable that a small trial be carried out before applying a full coat.

APPLICATION

Stir the liquid thoroughly and then add required Thinner to get required application viscosity. Strain the Primer by Nylon filter cloth of 400 mesh size then apply uniformly over the surface and stir again before and during application. Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with recommended thinner

Application: By Brush/By Air Spray

For Brush / Roller application, add a maximum of 5% thinner if required. Apply uniformly on the surface of the substrate. Use quality brushes for paint application.

For Air spray application:

Thinner: OMKAR GP THINNER

Addition: 10-15%

Nozzle Orifice: 1 .2 -1 .4 mm

Nozzle Pressure: 40-70 psi

HEALTH & SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant National Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during applying and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (i.e wear gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment. This is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes.

IMPORTANT NOTES

1. Do not apply paint when temperature falls below 10°C or rises above 50°C and when Relative Humidity is above 85%, Do not apply during rain, fog, or mist.
2. Brushes and spray equipment should be cleaned with recommended thinner otherwise equipment is liable to damage.
3. Volume Solids will vary depending on shades. Products with different volume solids are also available on request.
4. DFT variation can be obtained by change in application method/thinning ratio. Contact our representative for further assistance.
5. Shelf life indicated is minimum for this Product and it is subjected to re-inspection thereafter. Individual component is required to be store in cool, dry and covered condition, away from heat and ignition.

DISCLAIMER

The information contained within this Data Sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.